

PRODUCT DATA SHEET

www.bestor.ee
Bestor Grupp AS
Valdeku 168, 11217, Tallinn, Estonia
+372 518 0889

Mineroll BASE 3000A

Document number : BG1459

Publication Date: 23.03.2023 Revision date: 23.03.2023

| | | | | |
|---|---|-------------------|------------------|---------------|
| PRODUCT DESCRIPTION | Elastomeric modified bituminous waterproofing membrane | | | |
| USAGE | Used as underlay and intermediate layer to waterproof terraces and roofs. It can also be used for waterproofing and damp proofing of underground structures, basement and storage tanks. Type A - Type T | | | |
| APPLICATION METHOD | Torched. Please refer to application booklet | | | |
| TOP SURFACE | Polyethylene Film | | | |
| BOTTOM SURFACE | Polyethylene Film | | | |
| REINFORCEMENT TYPE | Polyester | | | |
| STORAGE | Rolls to be stored upright and away from heat | | | |
| ECOLOGICAL DATA | Can be used in natural atmosphere | | | |
| TEST | METHOD | UNIT | TOLERANCE | VALUES |
| Visible defects | EN 1850-1 | - | - | NONE |
| Length | EN 1848-1 | m | -0,03 | 10 |
| Width | EN 1848-1 | m | -0,02 | 1 |
| Straightness | EN 1848-1 | - | - | PASS |
| Unit of weight | EN 1849-1 | kg/m ² | ±0,2 | 3 |
| Watertightness | EN 1928 (method A 10kPa) | - | - | PASS |
| | EN 1928 (method B 60kPa) | - | - | PASS |
| Reaction to fire | EN 13501-1 | class | - | E |
| Shear resistance of joint | EN 12317-1 | N/50mm | - | NPD |
| Water vapour transmission properties | EN 1931 | - | min. | 20.000 |
| Tensile Strength (Longitudinal) | EN 12311-1 | N/50mm | -%10 ; +%50 | 600 |
| Elongation at break (Longitudinal) | EN 12311-1 | % | (-0 ; +20) | 30 |
| Tensile Strength (Transverse) | EN 12311-1 | N/50mm | -%10 ; +%50 | 400 |
| Elongation at break (Transverse) | TS EN 12311-1 | % | (-0 ; +20) | 30 |
| Resistance to impact | EN 12691 (method A) | mm | min. | NPD |
| Resistance to static loading | EN 12730 (method B) | kg | min. | NPD |
| Resistance to tearing (Longitudinal) | EN 12310-1 | N | ±50% | 150 |
| Flexibility at low temperature | EN 1109 (top surface) | °C | min. | -5 |
| | EN 1109 (bottom surface) | °C | min. | -5 |
| Flow resistance at elevated temperature(<2mm) | EN 1110 | °C | min. | 110 |
| Artificial Ageing | EN 1296/ EN 1928 (Method B 60kPa) | - | - | PASS |
| Resistance to chemicals | EN 1847/ EN 1928 (Method B 60kPa) | - | - | PASS |
| Dangerous substances | Doesn't contain asbestos or coal tar constituents. | | | |

NPD = (No performance defined)

* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0